

## Jojoy Indoor Strand Woven Bamboo Flooring Technical Data

<b>Test Results</b>	<b>Property</b>	<b>Unit</b>	<b>Requirement</b>	<b>Test data</b>	<b>Judgement</b>
	Moisture Content	%	6.0—14.0	9	Accept
	Bending Strength	MPa	$\geq 98.0$	120.9	Accept
	Rigidity (Hardness)	MPa	$\geq 55.0$	114.7	Accept
	Resistance to Surface Impact	mm	The Height of falling $\geq 1000$ , Diameter of impress $\leq 10$ , No crack	7.9 No crack	Accept
	Formaldehyde Emission	mg/L	$\leq 1.5$	0.1	E1

Zhejiang Jojoy Leisure Products Co., Ltd.